

PC 2041

Volume 37, No 5, 1996

ISSN 0043-2288

Welding in the World

*Journal of the International
Institute of Welding*

September/October 1996



Le Soudage dans Le Monde

*Revue de L'Institut
International de la Soudure*

Septembre/Octobre 1996



PERGAMON

ETHICS ETH-BIB



Analysis of results on improved welded joints

by I. Huther, H.P. Lieurade, R. Souissi, A. Nussbaumer, B. Chabrolin and J.J. Janosch (France)

Abstract

Recent studies have shown that the use of improvement techniques on welds allows an increase in the level of admissible fatigue strength (even more than 100%). The aim of this study was to collect and validate literature data, create a data base containing the joint characteristics and fatigue results, make a statistical analysis of the data in order to quantify the effect of parameters influencing the fatigue strength and propose new S-N curves which are compared to those given in Eurocode 3. Four improvement techniques (grinding, TIG dressing, hammer peening, shot peening) and four joint types (butt, T joints, cruciform and longitudinal joints) were taken into account. Joint thicknesses less than 25 mm loaded in air with a stress ratio R between 0 and 0.1 were selected. Three classes of yield strength for the base metal were considered. <400, 400-600, >600. All S-N curves were above those of as-welded assemblies. The best results were obtained with hammer peening. The larger increase in the fatigue strength due to the use of improvement techniques was due to the occurrence of an initiation phase in addition to the crack propagation phase. During the initiation phase, the extension of existing crack-like defects is slowed down or even stopped. The duration of this phase increases with the total fatigue life.

Keywords: Fatigue strength; TIG remelting; Hammers; Peening; Grinding; GTA welding; Statistical methods; Butt joints; Cruciform joints; T joints; Longitudinal welds; Crack initiation; Improvement techniques

Résumé

Des études récentes ont montré que l'utilisation de techniques de parachèvement des soudures permettent d'accroître la résistance admissible à la fatigue (jusqu'à plus de 100%). Le but de cette étude est de compiler et de valider les données de la littérature, de créer une base de données indiquant les caractéristiques des joints et leur résistance à la fatigue, d'effectuer une analyse statistique des données à fin de quantifier l'influence des paramètres influant sur la résistance à la fatigue et de proposer de nouvelles courbes S-N qui sont comparées à celles spécifiées dans l'Eurocode 3. Quatre techniques d'amélioration (meulage, refusion TIG, martelage et grenailage) et quatre types de joints (bout à bout, assemblages en T, assemblage en croix et joints longitudinaux) ont été pris en compte. Les épaisseurs considérées sont inférieures à 25 mm (solicitations à l'air ambiant) et le rapport

de charge R est de 0 et 0.1. Trois classes de limites d'élasticité ont été considérées: <400, 400-600 et >600 MPa. Toutes les courbes S-N étaient supérieures à celles des assemblages brut de soudage. Les meilleurs résultats ont été obtenus par martelage. L'augmentation de la résistance à la fatigue suite à ces traitements d'amélioration est due à l'apparition d'une phase d'initiation des fissures, en plus de la phase de propagation. Lors de la phase d'initiation, l'extension des fissures existantes est freinée et même stoppée. La durée de cette phase augmente avec la durée de vie totale en fatigue.

Mots clés: Résistance à la fatigue; Refusion TIG; Marteau; Martelage; Meulage; Soudage TIG; Méthodes statistiques; Joints bout à bout; Joints cruciformes; Assemblages en T; Soudures longitudinales; Initiation des fissures; Méthodes d'amélioration

1. Introduction

Recent studies show that the use of improvement techniques on welds allows an increase in the level of the admissible fatigue strength (even of more than 100%). The gain is particularly good when these techniques are used with high tensile steel.

The utilization of research results in industry, to take advantage of these techniques during design, requires the following:

- the specification of each improvement technique, defining the operational and control practices.
- the modification of actual design codes concerning the fatigue of welded joints which do not take into account the improvement techniques and the efficiency of high strength steels.

The target of this study is to collect the literature data and to provide a statistical analysis.

The study includes the following steps:

- collection and validation of literature data
- creation of a data base in the form of sheets containing the joint characteristics and fatigue results
- statistical analysis of the data base to quantify the effect of the parameters influencing the fatigue strength
- from the statistical analysis, proposal of new S-N curves.

2. Improvement techniques

The standard improvement techniques selected in this study are the following:

- grinding of the weld toe to suppress defects and improve the shape of the weld toe
- TIG dressing to eliminate weld toe defects and to increase the weld toe radius
- hammer peening on the weld toe to modify the local geometry and introduce a compressive field of residual stresses

IIW/ITS-1301-95 (ex doc. XIII-1691-95) Class A recommended for publication by IIW Commission XIII "Fatigue of welded components and structures" as the authors' own work.

I. Huther and H.P. Lieurade are at CETIM, France. R. Souissi, A. Nussbaumer and B. Chabrolin are at CTICM, France and J.J. Janosch is at IS, France.

- shot peening to introduce a compressive field of residual stresses without modifying the geometry.

3. Data base

The data used in this study are bibliographical, from national and international conferences, publications, IIW documents, French IS and CETIM documents.

To analyse the results published in these documents, a standard data sheet was established from the data sheet used to collect laboratory fatigue results proposed by Commission XIII of the IIW [1]. This data sheet includes four principal parts (see Appendix 1):

- chemical composition and mechanical properties of the base metal
- welding process, composition and properties of the filler metal
- characteristics of the improvement technique
- characteristics of joints and fatigue test results.

For each type of improvement technique, the characteristics are:

- for *grinding*: the type of grinding tool and its radius, the grinding direction, the number of passes and the ground depth
- for *TIG dressing*: the current intensity, the voltage, the electrode diameter, the speed of dressing, the gas flux and its composition, and the number of passes
- for *hammer peening*: the type of tool and its diameter, the pressure, the speed and the number of passes
- for *shot peening*: Almen intensity, the tension, the type of balls and their diameter, the overlap ratio and the number of passes.

Particular attention is given to the joint geometry (micro and macro). But there is little information on this point.

Based on 62 references for TIG dressing and shot peening and 39 for grinding and hammer peening, the number of homogeneous series of test results on steel existing in the data base is:

- for grinding: 84
- for TIG dressing: 96
- for hammer peening: 33
- for shot peening: 53

plus the combinations:

- stress release + TIG: 1 or
TIG + stress release: 5
- stress release + shot peening: 2 or
shot peening + stress release: 2
- TIG + shot peening: 2
- stress release + grinding + shot peening: 1
- hammer peening + grinding: 1
- grinding + stress release: 1
- grinding + shot peening: 1

plus the as-welded results to be used as reference (35).

Some 300 data sheets form the data base.

4. Parametric analysis

To analyse the content of the data sheets, data are grouped in the tables given in Appendix 2 versus improvement techniques and joint types with mention of the following parameters: yield strength, material, thickness, load condition, environment, stress ratio R and reference.

From these tables, for the four studied improvement techniques, we observe that:

- the majority of data concerns butt joints, T joints, cruciform and longitudinal non-load-carrying joints (Fig. 1)
- for a joint, there can exist different ranges of yield strength
- for a type of joint, the range of thicknesses is large
- fatigue testing in tension is predominant for the butt joints, cruciform and longitudinal non-load-carrying joints and in bending for T joints
- the stress ratios R are essentially 0 and 0.1, there are few tests at $R = -1$
- the tests are made in air essentially, few in sea water
- for a given material, there are few test results from different origins
- for a joint type and a material, there is, in most cases, only one thickness tested.

5. Statistical analysis of results

For all test results, whatever the improvement may be, the joint and the environment, the mean S-N curves were determined by a linear regression in log-log using S as function and N as variable.

If the population is homogeneous (little scatter), the linear regression in log-log using S as function is equivalent to the linear regression in log-log using N as function (used usually).

As the tests are heterogeneous (set of data different), to take S as variable leads to aberrant results, on the other hand, to take N as variable gives more coherent results.

These mean S-N curves are only used as guide to derive the slope corresponding to each improvement technique and type of joint.

5.1. Preliminary

The statistical analysis was made on butt joints, T joints, cruciforms and longitudinal non-load-carrying joints in air, since the results are not sufficient in the other cases for a statistical analysis.

These results were grouped by improvement techniques, by type of joints, according the stress ratio R ($0 \leq R \leq 0.1/R = -1/R > 0.1/-1 < R < 0$), the yield strength ($YS < 500$ MPa/ $YS > 500$ MPa), and the loading condition (tension and bending) in the tables given in Appendix 3.

From these tables, we observe that the majority of results are for $0 < R < 0.1$, and that there are few differences between the results in tension and those in bending.

5.2. Analysis

In the following, the study concerns butt welds, cruciform, T and longitudinal non-load-carrying fillet welds, in air, at R between 0 and 0.1, with thicknesses lower than 25 mm, and improved by one of the following improvement techniques: hammer peening, grinding, TIG dressing, and shot peening. We have considered three classes of yield strength of the base metal: $YS < 400$ MPa, $400 < YS < 600$ MPa and $YS > 600$ MPa.

In each case, the test results were plotted using $\log \Delta\sigma$ versus $\log N$ ($\Delta\sigma$ stress range and N number of cycles at failure). The S-N curves were modelled by $\log N = -m \cdot \log \Delta\sigma + \log C$: the slope m , the constant $\log C$ and the standard deviation of $\log C$ were calculated (Appendix 4). We have plotted the slope m and the value of $\Delta\sigma$ at 2×10^6 cycles versus of the joint type for each




Fig. 1. Types of joints

improvement technique and yield strength classes of the base metal (Figs 2 and 4).

From histograms of m (Fig. 2), we observe that:

- the slope of the S–N curves varies according to the improvement technique for the same joint and according to the joint type for a given improvement technique
- the difference between the slopes can be important for the same type of joint according to the improvement technique (e.g. cruciform joints) or for the same improvement technique according to the joint type
- the slope varies for the same joint and the same improvement technique when the yield strength varies (e.g. ground cruciform joint).

Because of the scatter of results (differences due to plate thicknesses, welding process, and experimental conditions), we have determined empirically the envelope curves superior and inferior





Fig. 2. Values of m deduced from mean curves (linear regression $\log \Delta\sigma - \log N$)




Fig. 3. Values of m deduced from inferior envelope curves (on coordinates $\log \Delta\sigma - \log N$)

to the test results so that these curves crossed at 10^4 cycles. The tables of Appendix 4 give the estimated values of m , and $\Delta\sigma$ at 2×10^6 cycles corresponding to the inferior envelope curve, for each improvement technique and joint.

The histograms of m and $\Delta\sigma$ at 2×10^6 cycles as a function of the joint type for each improvement technique and yield strength




Fig. 4. Values of $\Delta\sigma$ achieved on regression curve ($\log \Delta\sigma - \log N$) for 2×10^6 cycles




Fig. 5. Values of $\Delta\sigma$ deduced from inferior envelope curve (on coordinates $\log \Delta\sigma - \log N$) for 2×10^6 cycles

Table 1. Slope of S-N curves

Slope m	Butt joint (A)	Cruciform (D)	T joint (C)	Longitudinal (F)
Grinding	7	7	7	5
Hammer peening	10	10	10	8
TIG dressing	7	6	4	—
Shot peening	9	9	9	5

were plotted (Figs 3, 5). We observe that the slopes are smaller than those achieved by linear regression, but vary in the same way.

6. Proposed S-N curves

From the results of the regression analysis, the following slopes were derived. The slopes are independent of the yield strength (YS) and all greater than 3 (Table 1).

The classification of the m values by increasing order is in relation to the efficiency of the improvement technique. In all cases, m is greater than as-welded joints where $m = 3$.

Determination of design S-N curves is based on a statistical evaluation according to Eurocode 3 Annex Z [2]. The slope is imposed at the value in Table 1, thus all results may be transformed in stress ranges at 2×10^6 cycles. The analysis provides the following results (Table 2):

- $\Delta\sigma_m$ mean stress range (50% of probability of failure for 2×10^6 (cycles)
- s standard deviation associated with $\Delta\sigma_m$ (assumed log-normal)
- S_x stress range for 2×10^6 cycles and 5% of probability of failure (this characteristic value is an estimation with a 75% level of confidence)

Table 2. Improvement results

YS	Joint	Techniques	spe nb	m	$\Delta\sigma_m$	s	S_L	S_{RL}	S_{RK} (AW)	S_{RK}/S_{RK} (AW)
< 400	Butt joint	Hammer peening	30	10	222	15	195	193	90	2.1
		TIG dressing	=60	7	291	57	202	178		2.0
	Cruciform	Hammer peening	19	10	244	18	211	209	71	2.9
		TIG dressing	48	6	233	49	152	126		1.8
		Shot peening	66	9	196	28	150	144		2.0
	T joint	TIG dressing	25	4	164	20	127	124	71-90	1.7
Longitudinal	Grinding	45	5	164	29	115	103	63-90	1.6	
	Hammer peening	11	8	226	8	210	206		3.2	
	Shot peening	26	5	123	15	97	95		1.5	
400 <	Butt joint	TIG dressing	156	7	280	41	215	206	90	2.3
< 600	Cruciform	Grinding	25	7	195	17	164	162	71	2.3
		TIG dressing	154	6	273	58	182	155		2.2
T joint	TIG dressing	74	4	213	45	143	122	71-90	1.7	
	Shot peening	30	9	278	34	222	220		3.1	
> 600	Butt joint	Shot peening	99	9	326	52	242	226	90	2.5
	Cruciform	Shot peening	33	9	232	40	163	146	71	2.0
	Longitudinal	Shot peening	18	5	148	14	122	121	63-90	1.9




Fig. 6. Values of m fixed for characteristic curves $\log \Delta\sigma - \log N$ and corresponding levels of $\Delta\sigma$ (S_d) determined for 2×10^6 cycles

- S_d design stress range for 2×10^6 cycles. It is obtained by $S_d = \frac{S_L}{\gamma_{M_f}}$ where γ_{M_f} is a relevant safety factor determined to fulfil the required safety level (or safety index β)
- S_{RK} modified characteristic value obtained by $S_{RK} = S_d \cdot \gamma_{M_f} = S_k \frac{\gamma_{M_f}}{\gamma_{M_f}}$, where γ_{M_f} is the safety factor imposed by Eurocode 3, while γ_{M_f} has been determined by statistical analysis of test results. In that way, S_{RK} is the final value that may be adopted for the detail classification tables.
- S_{RL} (AW) is corresponding class (stress range for 2×10^6 cycles) for as-welded detail of Eurocode 3.

The statistical analysis is based on the assumption of independence between the sample mean and the sample standard deviation, and on $\Delta\sigma$ (or N) being log-normal. It may then be shown that the probability of any quantity $m-k \cdot s$ (m sample mean, s sample standard deviation) being lower than a given level is calculated from a non-centred Student's distribution, the parameters of which depend on the number of available test results.

We have plotted the imposed m and the corresponding $\Delta\sigma$ determined for 2×10^6 cycles, versus joint types and improvement techniques for each class of yield strength. $YS < 400$, $400 < YS < 600$, $YS > 600$ MPa (Fig. 6), and the S-N curves for each type of joint (Fig. 7).

From the S-N curves (Fig. 7), we observe that:

- All curves are above the Eurocode 3 curves corresponding to the as-welded joint, and exhibit a resistance increase due to improvement techniques.
- The S-N curves of improved joints in high tensile steel ($YS > 400$ MPa) are above or on those of improved joints in mild steel.
- For cruciform and longitudinal joints, the hammer peening gives the better results.




Fig. 7. Comparison between characteristic curves of Eurocode and those achieved in the case of improved joints for each joint type studied




Fig. 8. Comparison of efficiency of each improvement technique studied, versus joint type and yield strength level of base metal

Table 3. As-welded results

Joint	spe nb	m	$\Delta\sigma_m$	s	S_L	S_{Rk} (this study)	S_{Rk} (Eurocode 3)
Butt joint	100	3	136	30	92	86	90
Cruciform	91	3	124	28	81	73	71
T joint	66	3	140	28	98	94	71–90
Longitudinal	18	3	85	9	68	68	63–90

Table 4.

Joint	Techniques	m	S_{Rk}		S_{Rk} (AW)
			Re < 400	Re > 400	
Butt joint	TIG dressing	7	180	205	90
	Shot peening	9		225	
	Hammer peening	10	195		
Cruciform	TIG dressing	6	125	155	71
	Grinding	7		160	
	Shot peening	9	145	145	
	Hammer peening	10	210		
T joint	TIG dressing	4	125	125	71–90
	Shot peening	9		220	
Longitudinal	Grinding	5		105	63–71–90
	Shot peening	5	95	120	
	Hammer peening	8	200		

m: slope of S–N curve

S_{Rk} : design stress range of improvement joints

S_{Rk} (AW): Eurocode 3 design stress range of as-welded joints

- For butt joints, and the same steel (mild or high tensile strength) whatever the improvement may be, the results are similar (the S–N curves merge).

The S–N curves versus the improvement techniques were plotted in Fig. 8.

We observe that:

- for TIG dressing and shot peening, the S–N curves are different according to the joint; the better results are achieved for butt joints and the worse for longitudinal joints, according to the code classification of as-welded joints;
- for hammer peening, the S–N curves of each joint are close;
- for grinding, a great difference exists between the results according to the joint type.

7. Comparison between as-welded results and Eurocode 3

For each publication of improved results, as-welded results are given as reference. These as-welded tests are analysed by the same method of tests as improvement joints (Annex Z of the Eurocode 3). A single class of yield strength are given because the yield strength has no influence on S–N curve.

The slope of the S–N curve is imposed at 3, as in Eurocode 3, and the results may be transformed in stress range at 2×10^6 cycles. The analysis provides the results shown in Table 3.

The as-welded S_{Rk} are similar to those of Eurocode 3, therefore the comparison between improvement results and those of Eurocode 3 is justified.

For the butt joints, the experimental S_{Rk} is lower than that of Eurocode 3, perhaps because the test specimens were indistinctly aligned. This phenomenon is not negligible. For T joints, the test value is nearer to 90 than 71 because the load of testing is bending and not tension. For the other joints, the S_{Rk} values are the same.

8. Conclusion

This study collected literature data in the form of standard data sheets (some 300 sheets), to analyse them statistically and to establish S–N curves.

Four improvement techniques (*grinding, TIG dressing, hammer peening, shot peening*) for four joints (*butt, T joints, cruciform, and longitudinal joints*) were taken into account in this study.

After a preliminary analysis, we selected joints with *thickness smaller than 25 mm* loaded in air, with a stress ratio *R*, between 0 and 0.1. *Three classes of yield strength* of base metal ($YS < 400$, $400 < YS < 600$, $YS > 600$ MPa) were considered.

After a statistical analysis (linear regression of test results), we have fixed the slopes of the S–N curves for each joint type and improvement techniques whatever the yield strength may be. *All these slopes are greater than 3*. They were used to derive the design stress range S_{Rk} (Eurocode 3 method) at 2×10^6 cycles. *All the S–N curves achieved are above those of as-welded assemblies*. The better results are obtained with hammer peening.

In summary, we achieve the results shown in Table 4.

The rather large increase in the fatigue strength, due to the use of improvement techniques, can be explained by the occurrence of a so-called initiation phase in addition to the crack propagation phase. During the initiation phase, the extension of existing "crack-like" defects is slowed down or even stopped. The duration of this phase increases with the total fatigue life (or the decrease on the stress range). It explains the effect observed on the slope of the S–N curves.

References

1. Fatigue testing of welded components. *Welding in the World*, Vol. 29, No. 9/10, doc. IIS/ITW XIII-1090-90.
2. Eurocode 1, Annex Z: Informative determination of design resistance from tests, 1992.

Appendix 1

Standard data sheet

Specimen:

Thickness: mm Width: mm Length: mm

Observations:

Fatigue testing conditions:


Test machine: R = Temperature: Environment:
 Loading mode: Frequency:
 Wave form: σ_{mean} :

Nominal area:
 Failure criterion:
 Test results: $\Delta\sigma$ (2 x 10⁶ cycles/50%) = MPa s = MPa
 Ref: as welded

$\Delta\sigma$ (*) (MPa)	N (cycles)	Observations (**)

(*) DS = Nominal stress range
 (**) F: Failed specimen (toe or root)
 NF: Non failed at N cycles


$$\Delta\sigma \left(2 \times 10^6 \text{ cycles}/50\% \right) = \frac{\text{MPa}}{s} = \frac{\text{MPa}}{\text{MPa}}$$



$\rho =$ mm $\theta =$ °
 $l =$ mm $h =$ mm

Global geometry
 T = mm T₂ = mm
 W = mm W' = mm L' = mm

Type of joints:



Fatigue data sheet on welded joints

Title:

Authors:

Reference:

Parent material: Grade

--	--	--	--	--	--	--	--	--	--

Heat treatment

YS (MPa)	UTS (MPa)	E (%)	R.A.	KVC (J/cm ²)

Endurance limit at cycles R = $\Delta\sigma_0 =$ MPa s = MPa

Welding: Welding process Position Gas

Electrode	Flux	Position	Gas

YS	UTS	E	R.A.	KCV

Pass n°	Electrode size	Intensity (A)	Tension (V)	Speed (cm/mm)	Plate preparation	Preheat temperature

Improvement:

Surface treatment after welding

Mechanical treatment after welding

Intensity	Tension

Example of data sheet

Specimen:

Thickness: 25 mm Width: 75 mm Length: 825 mm

Observations:

Fatigue testing conditions:

Test machine: R = 0.1 Temperature: Environment: air
 Loading mode: 4 point bending Frequency: 30 Hz
 Wave form: σ_{mean}


Nominal area:
 Failure criterion: Crack initiation

Test results: $\Delta\sigma (2 \times 10^6 \text{ cycles}/50\%) = \text{MPa}$ $s = \text{MPa}$
 Ref: as welded

$\Delta\sigma^*$ (MPa)	N (cycles)	Observations (**)
353	1.2×10^5	F
333	1.7×10^5	F
314	1.4×10^5	F
275	10^6	F
255	10^7	NF
235	10^7	NF

(*) DS = Nominal stress range
 (**) F: Failed specimen (top or front)
 NF: Non failed at N cycles

$\Delta\sigma (2 \times 10^6 \text{ cycles}/50\%) = \text{MPa}$
 $s = \text{MPa}$




Local geometry

$p = 5.85 \text{ mm}$ $\theta = 42^\circ$
 $l = \text{mm}$ $h = \text{mm}$

Global geometry
 $T = 25 \text{ mm}$ $T_2 = 25 \text{ mm}$
 $W = \text{mm}$ $L' = \text{mm}$

Type of joints:



Fatigue data sheet on welded joints

Title: Improvements of fatigue strength in fillet welded joint b, CO₂ soft plasma are dressing on welded toe
 Authors: W. Shimada, S. Hoshinouchi, S. Hiramoto, A. Hijikata, S. Yoshioka, A. Inoue
 Reference: IIW-XIII-881-78

Parent material:

Grade HT 60

C	Si	Mn	P	S	Nb	Ni	Cr
0.16	0.45	1.42	0.018	0.006	0.06	0.01	0.02

Heat treatment

YS (MPa)	UTS (MPa)	E (%)	R.A.	KVC (J/cm ²)
421	588	43		

Endurance limit at 10^7 cycles $R = 0.1$ $\Delta\sigma_D = \text{MPa}$ $s = \text{MPa}$

Welding:

Electrode	Flux	Position
	Welding process CO ₂ semi-auto	Gas CO ₂

Chemical composition of the filler material

C	Si	Mn	P	S	Mo
0.16	0.38	0.87	0.012	0.009	0.41

Mechanical properties of the deposit material

YS	UTS	E	R.A.	KCV
570	657	26		

Pass n°

Electrode size	Intensity (A)	Tension (V)	Speed (cm/min)	Plate preparation	Preheat temperature
$\varnothing 1.2 \text{ mm}$	240	33	50		

Improvement:

Surface treatment after welding stress relieved at 625°C for 2h + TIG dressed

Mechanical treatment after welding

Intensity	Tension	\varnothing (mm)	Speed (cm/min)	Gas flow
250 A	14 V	3.2	14	Ar 10 l/min

Appendix 2 Part 1: Recapitulative tables of the data base, grouping the test versus improvement techniques and joint types with mention of the following parameters: yield strength, material, thickness, load condition, environment, stress ratio

Material	YS (MPa)	Improvement	Type of joints	Thickness (mm)	Load	$R = \frac{\sigma_{min}}{\sigma_{max}}$		Environment	References	
A42 FP	280	Mill grinding	Butt welded	10	Tension	-1		Air	23	
A 5083P-0 (aluminium)		Toe grinding	Butt welded	6	Bending	-1		Air	15	
		Laser remelting	Butt welded	6	Bending	-1		Air	15	
		Laser remelting (speed 100 mm/mn) (V)	Butt welded	6	Bending	-1		Air	15	
		Laser remelting (V = 100 mm/mn) (DFs = 2 mm)	Butt welded	6	Bending	-1		Air	15	
		Laser remelting (V = 800 mm/mn)	Butt welded	6	Bending	-1		Air	15	
		Laser remelting (V = 500 mm/mn) (DFs = 4 mm)	Butt welded	6	Bending	-1		Air	15	
AE 235	233	Hammer peening	Butt welded	12	Bending	0		Air	38	
AE 355	399	Hammer peening	Butt welded	12	Bending	0		Air	38	
BS 15	250	Light grinding	Longitudinal	12.7	Tension	0		Air	3, 33, 35, 36	
		Full grinding	Longitudinal	12.7	Tension	0		Air	3, 33, 35, 36	
		Full grinding	Longitudinal	12.7	Tension	0		Air	3, 33, 35	
		Light grinding	Cruciform	12.7	Tension	0		Air	3, 33, 34, 35, 36	
		Full grinding	Cruciform	12.7	Tension	0		Air	3, 33, 35, 36	
		Full grinding	Cruciform	12.7	Tension	0		Air	3, 33, 35	
		Full grinding	Longitudinal	12.7	Tensile	0		Air	33, 35	
		(full penetration welds)								
		Hammer peening	Longitudinal	12.7	Tensile	0		Air	33, 35	
		Hammer peening	Cruciform	12.7	Tensile	0		Air	33, 34, 35	
Hammer peening + full grinding	Cruciform	12.7	Tensile	0		Air	33, 35			
BS 968	340	Light grinding	Cruciform	12.7	Tensile	0		Air	3, 33, 35	
		Full grinding	Cruciform	12.7	Tensile	0		Air	33, 35	
		Full grinding	Cruciform	12.7	Tensile	-1		Air	33, 35	
		Full grinding	Longitudinal	12.7	Tensile	0		Air	33, 35	
		Hammer peening	Cruciform	12.7	Tensile	0		Air	33, 35	
BS 4360/43A	245	Disc ground	Cruciform	12.5	Tension	0		Air	3, 6, 38	
		Disc ground	Cruciform	12.5	Tension	-1		Air	3, 5, 38	
		Disc ground	Cruciform	12.5	Tension	0.5		Air	3, 5, 38	
		Toe burr ground	Cruciform	12.5	Tension	0		Air	3, 6, 38	
		Fully burr ground	Cruciform	12.5	Tension	0		Air	3, 6, 38	
		Disc ground	Cruciform	12.5	Tension	0		Air	3, 5	
		Hammer peening (4 passes)	Cruciform	12.5	Tension	0		Air	5, 18, 25	
		Hammer peening (4 passes)	Cruciform	12.5	Tension	-1		Air	5, 18, 25, 28	
		Hammer peening (4 passes)	Cruciform	12.5	Tension	0.5		Air	5, 18, 25, 28	
		Hammer peening (1 pass)	Cruciform	12.5	Tension	0		Air	6, 18	
		Hammer peening (2 passes)	Cruciform	12.5	Tension	0		Air	6, 18	
		Hammer peening (3 passes)	Cruciform	12.5	Tension	0		Air	6, 18	
		Hammer peening (4 passes)	Cruciform	12.5	Tension	0		Air	6, 18, 38	
		BS 4360/50A	333	Hammer peening (4 passes, Ø12)	Cruciform	13	Tension	0		Air
Hammer peening (2 passes, Ø6)	Cruciform			13	Tension	0		Air	8	
Hammer peening (4 passes, Ø6)	Cruciform			13	Tension	0		Air	8	
Hammer peening (8 passes, Ø12)	Cruciform			13	Tension	0		Air	8	
Hammer peening (8 passes, Ø6)	Cruciform			13	Tension	0		Air	8	

Appendix 2 Part I: Continued

Material	YS (MPa)	Improvement	Type of joints	Thickness (mm)	Load	$R = \frac{\sigma_{min}}{\sigma_{max}}$	Environment	References	
EH 36	360	Shallow burr grinding + disc grinding	Cruciform	10	Tension	0.1	Air	51	
			Cruciform	22	Tension	0.1	Air	51	
			Cruciform	40	Tension	0.1	Air	51	
			Cruciform	80	Tension	0.1	Air	51	
			T	22	3-point bending	0.1	Air	51	
			T	40	3-point bending	0.1	Air	51	
			T	80	3-point bending	0.1	Air	51	
		Toe grinding (burr) depth: 0.4	Cruciform	10	Tension	0.1	Air	51	
			Cruciform	22	Tension	0.1	Air	51	
			Cruciform	40	Tension	0.1	Air	51	
			Cruciform	80	Tension	0.1	Air	51	
			T	22	3-point bending	0.1	Air	51	
			T	40	3-point bending	0.1	Air	51	
			T	80	3-point bending	0.1	Air	51	
F		Local explosive treatment	Butt welded	12	Bending	—	Air	14	
Fe 510D or St 52-3	385	Multiple point peening	Longitudinal (gusset 100 mm)	20	Tension	0.1	Air	21-27	
		Simple point peening	Longitudinal (gusset 100 mm)	20	Tension	0.1	Air	21-27	
		Multiple point peening	Longitudinal (gusset 200 mm)	20	Tension	0.1	Air	21-27	
		Simple point peening	Longitudinal (gusset 200 mm)	20	Tension	0.1	Air	21-27	
H 75-3	810	Grinding	Butt welded	8		0	Air	20	
HSLA	472	Burr grinding	Longitudinal	20	Tension	0.1	Air	9, 22	
		Burr grinding	Reinforcement	20	Tension	0.1	Air	9, 22	
		Hammer peening (single point)	Longitudinal	20	Tension	0.1	Air	9, 22	
		Hammer peening (single point)	Reinforcement	20	Tension	0.1	Air	9, 22	
		Hammer peening (multiple points)	Longitudinal	20	Tension	0.1	Air	9, 22	
		Hammer peening (multiple points)	Reinforcement	20	Tension	0.1	Air	9, 22	
HT 50	390	Ground	Butt welded	12.7	Tension	0	Air	3	
		Ground	Butt welded	20	Tension	env. 0	Air	3	
		Ground	Butt welded		Tension	0	Air	38	
		Ground	Butt welded		Tension	0	Air	38	
HT 60	420	Ground	Cruciform	25	Bending	env. 0	Air	3	
HT 80	785	Ground	Cruciform	25	Tension	0	Air	3	
		Ground (MMA weld)	Butt welded	50	Bending	env. 0	Air	3	
		Ground (submerged arc weld)	Butt welded	50	Bending	env. 0	Air	3	
		Ground	Butt welded		Tension	0.05	Air	38	
		Ground			Tension	0.6	Air	38	
KE 36 (TMCP)	452-479	Ground	Cruciform	40	3-point bending	0	Air	12	
		Ground	(width 50 mm)						
		Ground (15 pass weld)	Cruciform	40	3-point bending	0	Air	12	
		Ground (6 pass weld)	Cruciform	(width 300 mm)	22	3-point bending	0	Air	12
			Cruciform		22	3-point bending	0	Air	12
Loycon QT	725	Ground	Cruciform	12.5	Tension	0	Air	3-31, 32, 35	
		Hammer	Cruciform	12.7	Tensile	0	Air	32, 32, 35	
SM 58 Q	556	Grinding (Ø6) grain 24	Cruciform	14	Tension	0	Air	1	
		Grinding (Ø12) grain 24	Cruciform	14	Tension	0	Air	1	
		Grinding (Ø6) grain 60	Cruciform	14	Tension	0	Air	1	
		Grinding (Ø12) grain 60	Cruciform	14	Tension	0	Air	1	
		Hammer peening (Ø3) 1 pass	Cruciform	14	Tension	0	Air	1	

Appendix 2 Part 1: Continued

Material	YS (MPa)	Improvement	Type of joints	Thickness (mm)	Load	$R = \frac{\sigma_{min}}{\sigma_{max}}$		Environment	References
						σ_{min}	σ_{max}		
BS 4360/50B	400	Hammer peening (4 passes)	Cruciform	13	Tension	0		Air	8
		Hammer peening (4 passes) + spot heated (1 pass for weld)	Cruciform	13	Tension	0		Air	8
		Hammer peening (4 passes) + spot heated (2 passes for weld)	Cruciform	13	Tension	0		Air	8
BS 4360/50C		Grinding (depth 2.5 mm, full width)	T	12.5	Tensile	0		Air	30
		Grinding (depth 4.2 mm, full width)	T	12.5	Tensile	0		Air	30
		Grinding (depth 2.5 mm, full width)	Cruciform	12.5	Tensile	0		Air	30
		Grinding (depth 2.5 mm, partial width)	T	12.5	Tensile	0		Air	30
		Grinding (depth 4.2 mm, partial width)	T	12.5	Tensile	0		Air	30
		Grinding (depth 6.25 mm, partial width)	T	12.5	Tensile	0		Air	30
BS 4360/50D	345	Disc ground	Cruciform	38	Bending	0.1		Air	2, 3, 4, 17, 37, 38
		Grinding	Cruciform	38	Bending	0.1		Sea water	2, 38
		Disc ground	Cruciform	25	Tension	0		Air	2, 3, 38
		Disc ground	Cruciform	38	Bending	0		Precored cathodic protection	2, 4, 17, 37
		Disc ground	Cruciform	38	Bending	0		Cathodic protection	2
BS4360/50D	345	Grinding	T	30	Bending	0.05		Air	7
		Hammer peening	Cruciform	25	Tension	0		Air	2-38
		Hammer peening	Cruciform	38	Bending	0		Air	2, 4-38
		Hammer peening	Cruciform	38	Bending	0		Sea water with cathodic protection	2, 4
		Grinding	T	50	4-point bending	0		Air	24
		Grinding	T	100	4-point bending	0		Air	24
BS 4360/50E	379	Grinding (burr) after precracking	Pipe	16	Bending	-1		Air	29, 39
		Grinding (burr) after repair weld 50%	Pipe	16	Bending	-1		Air	28, 29
		Grinding (burr) repair weld 100%	Pipe	16	Bending	-1		Air	28, 29
BS 5500/API X60	410- 490	Burr grinding	Pipe	8, 14	Pressure				10
E 355	370	Grinding	T	30	Bending	0.1		Air	2
E 355 KT	410	Grinding	T	40	Bending	0.1		Air	2-38
		Grinding	T	40	Bending	0.1		Sea water	2-38
E 335 R	430	Mild grinding	Butt welded	8	Tension	-1		Air	23
SS 41	256- 269	Hammer peening Ø10 $P = 4 \text{ kg/cm}^2$	Butt welded	13	Tension	0		Air	19
		Hammer peening Ø10 $P = 5 \text{ kg/cm}^2$	Butt welded	13	Tension	0		Air	19
		Hammer peening Ø8 $P = 4 \text{ kg/cm}^2$	Butt welded	13	Tension	0		Air	19
		Hammer peening Ø4 $P = 1.5 \text{ kg/cm}^2$	Butt welded	13	Tension	0		Air	19
		Machining Ø10	Butt welded	13	Tension	0		Air	19
		Grinding Ø180	Butt welded	4.5	Tension	-1		Air	50

Appendix 2 Part I: Continued

Material	YS (MPa)	Improvement	Type of joints	Thickness (mm)	Load	$R = \frac{\sigma_{min}}{\sigma_{max}}$	Environment	References
Statoil I	302	Toe grinding	T	30	Bending	0.1	Air	11
		Toe grinding + shot peening	T	30	Bending	0.1	Air	11
		Grind	T	30	3-point bending	0.1	Air	13
		Grind	T	100	Cantilever bending	0.1	Air	13
		Grind	T	160	3-point bending	0.1	Air	13
Superelso 70	685	Disc ground	Cruciform	12.5	Tension	0	Air	3, 6
		Toe burr ground	Cruciform	12.5	Tension	0	Air	3, 6-38
		Fully burr ground	Cruciform	12.5	Tension	0	Air	3, 6
		Hammer peening 4 pass Ø12	Cruciform	12.5	Tension	0	Air	6, 18-38
Ti6Al4V titanium		Grinding weld plasma arc	Butt welded	12.7	Tension	$S_m = 250$	A3 sea water synt.	16
		Grinding weld electron beam	Butt welded	12.7	Tension	$S_m = 250$	A3	16

References to Appendix 2 Part 1

- Sub-Committee: "Improving the fatigue strength of welded joints by various weld toe treatments". Methods of improving the fatigue strength of welded joints by various toe treatments. Society of Steel Construction of Japan, IIW doc. XIII 1289-88.
- A. Bignonnet: Improving the fatigue strength of welded steel structures. *Steel in Marine Structures*, 1987, pp. 99-118.
- G.S. Booth: Improving the fatigue strength of welded joints by grinding. Techniques and benefits. Welding Institute Report No. 268/1985. March 1985. IIW doc. XIII-1340-89.
- G.S. Booth: Techniques for improving the corrosion fatigue strength of plate welded joints. *Steel in Marine Structures*, 1987, pp. 747-757.
- G. S. Booth: The fatigue life of ground or peened fillet welded steel joints the effect of mean stress. *Metal Construction*, Vol. 13, No. 2, pp. 112-115, Feb. 1981.
- J.W. Knight: Improving the fatigue strength of fillet welded joints by grinding and peening. Welding Institute, 8/1976/E, March 1976. IIW doc. XIII 851-77.
- B. Lian: The National Norwegian Research program on steels for offshore structures. *Steel in Marine Structures*, 1987, pp. 19-27.
- S.J. Maddox: Aspects of the improvement in fatigue strength of fillet welds by peening. Welding Institute 261/1985. Feb. 1985.
- I.F.C. Smith, W.J. Muster, U. Bremen: Residual stresses and fatigue strength improvement of welded connections. Paper 19 presented at Conference "Effects of fabrication related stresses", Sept. 1985.
- A. Sys: Fatigue resistance of pressure vessels in high strength steel: effect of some improvement techniques. WT CM-CRIF MT 176. May 1989.
- P.J. Haagensen, A. Dragen, T. Slind, O. Ojhasacter: Prediction of the improvement in fatigue life of welded joints due to grinding, TIG dressing weld shape control and shot peening. *Steel in Marine Structures*, 1987, pp. 689-698.
- K. Matsuoka, I. Takamashi, T. Yoshii, E. Fujii: Effect of residual stress on fatigue strength of non-load carrying fillet welded joints. *Welding International*, Vol. 5, No. 12, pp. 936-943, 1991.
- O. Orjasacter, A. Dragen, P.J. Haagensen, B. Lian, A. Gunletksrud: Effect of plate thickness on the fatigue properties of a low carbon micro-alloyed steel. *Steel in Marine Structure*, 1987, pp. 315-335.
- S. Hristov, P. Petrov, S. Zvetanov: Reduction and redistribution of the residual welding stresses through local explosive treatment, 1986.
- I. Masumoto, M. Kutsuna, M. Hasegawa: The effect of laser remelting weld toes on the fatigue strength of aluminium alloy A5083P-O welded joints. *Welding International*, No. 11, 1989.
- J.P. Doucet, J. Guesnon, J. Charles: Corrosion fatigue behaviour of Ti-6Al-4V for marine application. Proceedings of the International Conference on Titanium, 1986.
- A. Bignonnet: Corrosion fatigue of steel in marine structures: a decade of progress. *Steel in Marine Structures*, 1987, p. 115.
- S.J. Maddox: Improving the fatigue strength of welded joints by peening. *Metal Construction*, April 1985.
- I. Masumoto, K. Matsuda, H. Iwata, M. Hasegawa: Effect of prestrain and hammer peening on fatigue strength. Improvement of mild steel welded joint. *Transactions of the Japan Welding Society*, Vol. 15, No. 2, Oct. 1984.
- H.J. Spies, K. Rössler, M. Starcevic: Improving the fatigue limit of butt welds in high tensile bainitic structural steel. *Welding International*, No. 4, 1987.
- U. Bremen: Amélioration du comportement à la fatigue d'assemblages soudés. Etude et modélisation de l'effet de contraintes résiduelles. Thèse no 787, Département de Génie Civil, Ecole Polytechnique Fédérale de Lausanne, 1989.
- U. Bremen, I.F.C. Smith, W.J. Muster: Erhöhung der Ermüdungsfestigkeit geschweisster Verbindungen. *Material und Technik*, No. 3, 1984.
- H.P. Lieurade, J.C. Tourrade: Effet des traitements de parachèvement sur le comportement en fatigue des joints soudés bout à bout en acier HLES. *Soudage et Techniques connexes*, Nov, Déc. 1984.
- G.S. Booth: The fatigue properties of plate welded joints of various thicknesses. American Society of Mechanical Engineers, Vol. 3A, 1990.
- S.J. Maddox: Improving the fatigue strength of welded joints. In *Fatigue Strength of Welded Structures*, Ch. 5, 1991.
- N. Gregory: Toe dressing. *Connect*, p. 5, Aug. 1990.
- U. Bremen, I.F.C. Smith, M.A. Hirt: Crack growth behaviour in a weld joint improved by residual stress methods. Paper 17. Proceedings of International Conference, April 1987.
- P.J. Tubby: *Fatigue Performance of Repaired Tubular Joints Containing Weld Repairs* Elsevier Science, 1990.
- P.J. Tubby: Fatigue performance of repaired tubular joints. Report, OTM 89 307, 1989.

30. J.G. Wylde, J. Haswell: Fatigue of fillet welds with toe cracks removed by grinding. Paper 61, Proceedings of International Conference. April 1987.
31. F. Watkinson, P.H. Bodger, J.D. Harrison: The fatigue strength of welded joints in high strength steels and methods for its improvement. *Fatigue Performance of Welded High Strength Steels*. C215/16/70.
32. J.D. Harrison: Techniques for improving the fatigue strength of welded high strength steels. *Fatigue Performance of Welded High Strength Steels*. C215/7/68.
33. T.R. Gurney: Effect of peening and grinding on the fatigue strength of fillet welded joint. *British Welding Journal*, Dec. 1968.
34. J.D. Harrison: Further techniques for improving the fatigue strength of welded joints. *British Welding Journal*, Nov. 1966.
35. J.D. Harrison: A summary of techniques for improving the fatigue strength of welded structures and an estimate of their cost. *Fatigue Performance of Welded High Strength Steels*. C215/12/69.
36. T.R. Gurney, S.J. Maddox: A re-analysis of fatigue data for welded joints in steel. *Welding Research International*, Vol. 5, No. 3, p. 63. 1975.
37. G. S. Booth: Constant amplitude fatigue tests on welded steel joints performed in sea water. European Offshore Steels Research Seminar, paper 9. 1978.
38. A. Bignonnet: Influence des traitements d'amélioration du pied des cordons de soudure sur la tenue à la fatigue des joints soudés. *Bulletin Technique du Bureau Veritas*, août/septembre 1984.
39. P.J. Tubby, J.G. Wylde: Remedial grinding a viable repair technique for fatigue cracks in tubular joints presented at the 22nd Annual Offshore Technology Conference, 7-10 May 1990.
40. I.F.C. Smith, U. Bremen, M.A. Hirt: Fatigue threshold and improvement of welded connections. *Fatigue* 84.
41. D.W. Hoepfner: Evaluation of possible life improvement methods for aluminium-zinc-magnesium fillet-welded details. *Fatigue Testing of Welded Material* ASTM STP 648, pp. 73-88, 1978.
42. G.S. Booth *Techniques for Improving the Corrosion Fatigue Strength of Plate Welded Joints*. Elsevier Science, Amsterdam, 1987.
43. J.F. Flavenot, A. Andrzejewski, M. Bramat: Influence des traitements de parachèvement et de surcharge sur la tenue en fatigue des assemblages soudés. 9ème journée Nationale sur le Grenailage de Précontrainte. SENLIS, CETIM, 27 Nov. 1985.
44. I.J. Polmear: Influence of peening on the fatigue performance of aluminium alloy fillet welds. IIW doc. 1976-MTC.
45. M.G. Faulkner, D.G. Bellow: Improving the fatigue strength of butt welded steel joints by peening. Vol. 5, No. 3. 1975.
46. P. Simon, A. Bragard: Amélioration des propriétés de fatigue des joints soudés. Recueil de recherches acier, rapport final. 1978.
47. Y. Itoh: Fatigue life prediction for GMA welded butt joints in a C-Mn-Si steel. Heavy Apparatus Engineering Laboratory, Toshiba Corp., Feb. 1987.
48. J. Yagi, Y. Tomita, S. Machida, M. Matoba, I. Soya: Thickness effect criterion for fatigue strength evaluation of welded steel structures. 1991 OMAE, Vol. III-B. Materials Engineering, ASME. 1991.

Appendix 2 Part 2: Improvement technique: TIG (Tungsten Inert Gas)

Type of joint: Butt joint

YS (MPa)	Material	Thickness (mm)	Load	$R = \frac{\sigma_{\min}}{\sigma_{\max}}$	Environment	Conditions	Reference
233	AE235	12	4-point bending	0	Air	Manual Auto	2 2
382	HT50A	12.7	Tension	0	Air		25, 46
	HT50B	20	Tension	0	Air		25, 46
385	PN72/484018	12	Tension	-1 -0.5 -0.3	Air Air Air	Standard welding Controlled weld	23 23 23 23
399	AE355	12	4-point bending	0	Air	Manual Auto	2 2
		8	Tension	0	Air	Manual	2
550	E490	8	Tension	0.1	Air		13, 14 3, 28, 36
629	St 51V	15	Tension	0	Air		62
769	St 70V	15	Tension	0 -1	Air Air		62 62
824	HT80A	25	Tension	$\sigma_{\min} \cdot 8$	Air	5 kJ/cm 15 kJ/cm 15 kJ/cm + 200°C 25 kJ/cm + 200°C	25, 46 25, 46 25, 46 25, 46
878	St 90V	15	Tension	0	Air		62

Type of joint: Overlap

YS (MPa)	Material	Thickness (mm)	Load	$R = \frac{\sigma_{\min}}{\sigma_{\max}}$	Environment	Conditions	Reference
226	S1312	10	Tension	$\sigma_{\min} = 14$ $\sigma_{\min} = 83$	Air Air		34 34
465	DOMEX400	10	Tension	$\sigma_{\min} = 14$ $\sigma_{\min} = 124$	Air Air		34 34
472	HLSA	20	Tension	0.1	Air		53 22, 53
796	OX802	10	Tension	$\sigma_{\min} = 14$ $\sigma_{\min} = 235$	Air Air		34 34

Appendix 2 Part 2: Continued

Improvement technique TIG (Tungsten Inert Gas)

Type of joint: T joint

YS (MPa)	Material	Thickness (mm)	Load	$R = \frac{\sigma_{\min}}{\sigma_{\max}}$	Environment	Conditions	Reference
302	Statoil	160	3-point bending	0.1	Air		11
340	Statoil	70	Cantilever bending	0.1	Air		11
341	Statoil	100	3-point bending	0.1	Air		11
350	52-3 St 52E	27	4-point bending	0.1	Air		40
		28	4-point bending	0	Air		48
360	SS400	30	3-point bending	0.1	Air	1-pass weld	60
						2-pass weld	60
						1-pass weld root crack	60
						1-pass weld bad condition	60
368	Statoil	30	3-point bending	0.1	Air		11
			4-point bending	0.1	Air		39
409	Fe 510 (BS 4360D)	40	4-point bending	0.1	Air		49, 50
					Sea water		49, 50
490	OX602	30	4-point bending	0.1	Air		40
					Sea water		40
					Sea water + cathode		40
500	E460	40	3-point bending	0.1	Air		20, 41
					Sea water + cathode		20, 41
518	FG47CT	27	4-point bending	0.1	Air		40
540	E460	40	3-point bending	0.1	Air		47
					Sea water + cathode		47
706	E690	8	4-point bending	0.1	Air		54
754	E690	10	4-point bending	0.1	Air		44
			3-point bending	0.1	Air		44
775	E690	10	4-point bending	0.1	Air		15, 44

Type of joint: Longitudinal non-load-carrying joint

YS (MPa)	Material	Thickness (mm)	Load	$R = \frac{\sigma_{\min}}{\sigma_{\max}}$	Environment	Conditions	Reference
628	E560TM	6	Tension	-1	Air	Weld $\phi = 1.6$ mm	35
				$I = 0.99$	Air	Weld $\phi = 1.6$ mm	35
				AV			
				-1	Air	Weld $\phi = 4$ mm	35
			$I = 0.99$	Air	Weld $\phi = 4$ mm	35	
			AV				

Appendix 2 Part 2: Continued

Improvement techniques: TIG dressing (Tungsten Inert Gas)

Type of joint: Cruciform joint

YS (MPa)	Material	Thickness (mm)	Load	$R = \frac{\sigma_{\min}}{\sigma_{\max}}$	Environment	Conditions	Reference
100	5086H111	6	Tension	0.1	Air	With chamfer With chamfer	31, 32 31, 92
250	AS1204	25	Tension	0.3	Air		52
254	AE235	8	Tension	0 -1	Air	Auto Manual Auto Manual	4, 5, 38 4, 9, 38 4, 9, 38 4, 5, 35
345	BS4360-50D	25 38	Tension 4-point bending	0 0	Air Air		16 16
372	BS4360-50D	30	Cantilever bending	0	Air Sea water		9 9
387	AE355	8	Tension	0 -1	Air Air	Auto Manual Auto Manual	4, 5, 38 4, 9, 38 4, 5, 38 4, 9, 38
423	SM41B	14	Tension	$\sigma_{\min} = 18$	Air Sea water		12 12
549	SM58Q	14	Tension	0 $\sigma_{\max} = \sigma_v$	Air Air		37 37
559	SM58Q	16	Tension	$\sigma_{\max} = \sigma_y$	Air	Weld $\phi = 2$ mm Weld $\phi = 2.6$ mm Weld $\phi = 3.2$ mm	61 61 61
726	HT80C	13	Tension	$\sigma_{\min} = 18$	Air		33
764	HT80	30	Cantilever bending	0	Air Sea water + cathode		9 9 9
769	St 70V	15	Tension	0	Air		62
775	E690	10	Tension	0.1	Air With chamfer With chamfer		15, 44 44 44
814	HT80B	16	Tension	$\sigma_{\min} = 18$	Air	Auto $d = 10$ mm $d = 15$ mm $d = 5$ mm $d = 0$ mm $d = 25$ mm	25, 46 33 33 33 33 33
880	KF23M14B	8	Bending	0.1	Air		10

Type of joints: Lap-joint

YS (MPa)	Material	Thickness (mm)	Load	$R = \frac{\sigma_{\min}}{\sigma_{\max}}$	Environment	Conditions	Reference
628	E560TM	6	Tension	-1	Air	1.4 kJ/mm 1 kJ/mm 0.7 kJ/mm	35 35 35

Appendix 2 Part 2: Continued

Improvement technique: Shot peening

Type of joint: Butt joint

YS (MPa)	Material	Thickness (mm)	Load	$R = \frac{\sigma_{\min}}{\sigma_{\max}}$	Environment	Conditions	Reference
100	5086H111	5.5	Tension	0.1	Air	Glass ball Ceramic ball Steel ball	31, 32 31, 32 3, 32
430	7075T73	30	Tension	0.1	Air		7
431	7075T6	10	Tension	0.1	Air	Rounded pins Ball	8 8
550	E490	8	Tension	0.1	Air		3, 28, 36
629	St 51V	15	Tension	0	Air		62
769	St 70V	15	Tension	0	Air		62
878	St 90V	15	Tension	0	Air		62
890	E890	50	Tension	0	Air	Ball Mi550 Ball S460	26 26

Type of joint: T joint

YS (MPa)	Material	Thickness (mm)	Load	$R = \frac{\sigma_{\min}}{\sigma_{\max}}$	Environment	Conditions	Reference
368	Statoil	30	4-point bending	0.1	Air		39
460	E460	30	3-point bending	0.1	Air		3, 28, 36 17, 30 27 20–22 Almen 45
500	E460	40	3-point bending	0.1	Air Sea water + cathode		20, 41 20, 41
			Bending (A.V.)	-1 -1	Air Air		20, 41 20, 41
515	E460	30	3-point bending	0.1	Air		27
540	E460	40	3-point bending	0.1	Air Sea water + cathode		47 0.7
550	E550	20	3-point bending	0.1	Air		45 3, 28, 36
560	E550	20	3-point bending	0.1	Air		17, 30
775	E690	10	3-point bending	0.1	Air		15, 44
			4-point bending	0.1	Air		15, 44

Type of joint: Longitudinal joint

YS (MPa)	Material	Thickness (mm)	Load	$R = \frac{\sigma_{\min}}{\sigma_{\max}}$	Environment	Conditions	Reference
355	Al-Zn-Mg	9.5	Tension	$\sigma_{\min} = 31$	Air		19
262	BS4360-43A	12.5	Tension	0	Air		57, 58
379	Fe510	20	Tension	0.1	Air		55
392	BS4360-50B	20	Tension	0	Air		57, 58
395	Fe510	20	Tension	0.1	Air		56
727	QT445A	20	Tension	0	Air		57, 58
824	RQT700	12.5	Tension	0	Air		57, 58

Appendix 2 Part 2: Continued

Improvement technique: Shot peening

Type of joint: Cruciform joint

YS (MPa)	Material	Thickness (mm)	Load	$R = \frac{\sigma_{\min}}{\sigma_{\max}}$	Environment	Conditions	Reference
100	5086H111	6	Tension	0.1	Air	Without chamfer glass ball Ceramic ball Steel ball With chamfer glass ball Ceramic ball Steel ball	31, 32 31, 32 31, 32 31, 32 31, 32 31, 32
250	Mild material	—	Tension	0	Air	Weld $\phi = 0.5-1$ 0.012-0.016 A 0.016-0.02 A	51 51 51
262	BS4360-43A	12.5	Tension	0	Air		57, 58
345	BS4360-50D	38	Cantilever bending	0	Air	0.016-0.02 A 0.024-0.028 A	43 43
					Sea water Sea water + cathode		43 43
360	E36-4	30	Tension	0.1	Air		18
373	BS4360-50B	13	Tension	0	Air	MIG $\phi = 0.6$ 0.012-0.016 A	6
380	BS4360-50B	13	Tension	0	Air	MMA $\phi = 0.8$ 0.012-0.016 A	6
390	BS4360-50B	—	Tension	-1 0 0.5	Air Air Air		51 51 51
392	BS4360-50B	12.5	Tension	0	Air		57, 58
396	BS4360-50B	13	Tension	0	Air	MMA $\phi = 0.6$ 0.012-0.016 A MMA $\phi = 1$ 0.015-0.019 A	6
397	BS4360-50B	13	Tension	0	Air	MMA $\phi = 0.6$ 0.012-0.016 A MMA $\phi = 0.8$ 0.024-0.028 A	6
400	BS4360-50B	13	Tension	0	Air	MIG $\phi = 0.6$ 0.012-0.016 A MIG $\phi = 0.8$ 0.012-0.016 A	6 6
769	St 70V	15	Tension	0	Air		62
775	E690	10	Tension	0.1	Air		15, 44
824	RQT700	13	Tension	0	Air		6

Type of joint: Lap-joint

YS (MPa)	Material	Thickness (mm)	Load	$R = \frac{\sigma_{\min}}{\sigma_{\max}}$	Environment	Conditions	Reference
409	E36	—	4-point bending	0.1	Air		29

Appendix 2 Part 2: Continued

Improvement technique: Combination

Type of joint: Butt joint

YS (MPa)	Material	Thickness (mm)	Load	$R = \frac{\sigma_{\min}}{\sigma_{\max}}$	Environment	Conditions	Reference
430	7075T73	30	Tension	$\sigma_{\max} = 200$	Stress release + shot	Flattened sol A3 sol A3	42 42
				0.1	Shot + stress release	2 h to 150°C 4 h to 150°C 60 h to 150°C 4 h to 160°C	7 7 7 7
337	A42FP	8	4-point bending	0.1	TIG + stress release		59
550	E490	8	Tension	0.1	Stress release + grinding + shot		13, 14
629	St 51V	15	Tension	0	TIG + stress release		62
769	St 70V	15	Tension	0	TIG + stress release Shot + stress release TIG + shot		62
878	St 90V	15	Tension	0	TIG + stress release		62
960	TA6V	12.7	Tension	$\sigma_a = 140$	TIG + shot		1

Type of joint: Cruciform joint

YS (MPa)	Material	Thickness (mm)	Load	$R = \frac{\sigma_{\min}}{\sigma_{\max}}$	Environment	Conditions	Reference
360	E36-4	30	Tension	0	Stress release + shot		18
396	BS4360-50B	13	Tension	0	Stress release + shot		6
421	HT60	25	4-point bending	0.1	Stress release + TIG		24
769	St 70V	15	Tension	0	Shot + stress release TIG + stress release TIG + shot		62 62 62

Type of joint: Longitudinal joint

YS (MPa)	Material	Thickness (mm)	Load	$R = \frac{\sigma_{\min}}{\sigma_{\max}}$	Environment	Conditions	Reference
355	Al-Zn-Mg	9.5	Tension	$\sigma_{\min} = 31$	Grinding + shot		19

References to Appendix 2 Part 2

1. J. Guesnon, J.P. Doucet, G. Chalon: Amélioration de la résistance à la fatigue du TA6V et de joints soudés par grenailage de précontrainte. 9^e Journée Nationale sur le Grenailage de Précontrainte. CETIM, Senlis. 27 Nov. 1985.
2. P. Simon, A. Bragard: Amélioration des propriétés de fatigue des joints soudés. Convention N6210-45/2/202. EUR 5974. 1978.
3. L. Picquet, A. Bignonnet, H.P. Lieurade: Amélioration par grenailage de précontrainte de la tenue à la fatigue des joints soudés. 9^e Journée Nationale sur le Grenailage de Précontrainte. CETIM, Senlis. 27 Nov. 1985, p. 149. *Construction Métallique*. Vol. 23, No. 4, p. 79. 1986.
4. P. Simon, A. Bragard: Amélioration par la refusion à la torche TIG. *Revue de la Soudure*, p. 263, 1978.
5. P. Simon, A. Bragard: Amélioration par la refusion TIG des propriétés de fatigue des joints soudés. *Revue de Métallurgie*. p. 727, Nov. 1979.
6. S.J. Maddox: Aspects of the improvement in fatigue strength of fillet welds by peening. Welding Institute, Feb. 1985. IIW doc. XIII-1339-89.
7. M. Bousseau, G. Brault, C.H. Mas: Conséquence des maintiens isothermes sur la tenue en fatigue d'assemblages soudés grenailés. IIW doc. XIII-1165-85.
8. M. Bousseau: Contribution à l'étude de l'influence d'opérations de parachèvement sur la tenue en fatigue des joints soudés. IIW doc. XIII-1111-83.
9. A. Narumoto: Corrosion fatigue strength of cruciform welded joints in synthetic seawater. Research Laboratories, Kawasaki Corporation, Japan. IIW doc. XIII-1123-84.
10. P.J. Haagensen: Effect of tungsten inert gas dressing on fatigue performance and hardness of steel weldments. Fatigue Testing of Weldments. ASTM STP 648, 1978.
11. O. Ørjasaeter, A. Dragen, P.J. Haagensen, B. Lian, A. Gunleiksrud: Effect of plate thickness on the fatigue properties of a low carbon microalloyed steel. Steel in Marine Structures. Delft, 15–18 June 1987.
12. R. Todoroki, M. Hanzawa, T. Ishiguro, S. Yanagimoto: Effects of toe profile improvement on corrosion fatigue properties of welded joint. Nippon Steel Corporation, July 1978, IIW doc. XIII-875-78.
13. H.P. Lieurade, J.C. Tourade: Effet des traitements de parachèvement sur le comportement en fatigue des joints soudés bout à bout en acier HLE. *Soudage et Techniques Connexes*, p. 398, Nov./Dec. 1984.
14. H.P. Lieurade, M. Wyseur: Effet de traitements de parachèvement sur le comportement en traction ondulée d'assemblages bout à bout en acier HLE. IRSID, Sept. 1983, ref. 1025.
15. H.P. Lieurade, P. Castellucci, J.F. Flavenot, J. Lu, G. Bel: Efficacité des traitements de parachèvement vis à vis de la résistance à la fatigue en fonction du type d'assemblages soudés en acier HLE. CETIM 30-09-91.
16. G.S. Booth: Essais de fatigue dans l'air à amplitude constante de joints en acier soudés (Constant amplitude fatigue tests on welded steel joints performed in air). European Offshore Steels Research, 27–28 Nov. 1978.
17. A. Bignonnet, H.P. Lieurade, L. Picquet: Etude de la fatigue des assemblages soudés en acier à haute limite d'élasticité dans le cas des structures offshore. EUR 9900FR, 1986.
18. P. Castellucci: Etude de l'influence d'un traitement de parachèvement sur la tenue en fatigue des joints soudés. IS no. 2450/295. COREM no. 83–02.
19. D. Webber: Evaluation of possible life improvement methods for aluminium–zinc–magnesium fillet-welded details. Fatigue Testing of Weldments. ASTM STP 648, 1978.
20. A. Bignonnet, H.P. Lieurade, C. Vallet: Fatigue des assemblages soudés en acier HLE dans les structures offshore. IRSID RCA 90301, Sept. 1989. Recherche CECA no. 7210 KG/302.
21. A. Sys: Fatigue resistance of pressure vessels in high strength steels effect of some improvement techniques. WT CM-CRIF MT 176, May 1989.
22. I.F.C. Smith, U. Bremen, M.A. Hirt: Fatigue thresholds and improvement of welded connections. 2nd International Conference on Fatigue and Fatigue Thresholds. UK. 3–7 Sept. 1984 (*Fatigue 84*, Vol. III).
23. Z. Zaczek: Improvement in the fatigue strength of butt welded joints by TIG remelting of weld reinforcements. *Metal Construction*. Vol. 16, No. 7, p. 423. July 1984.
24. W. Shimada, S. Hoshinouchi, S. Hiramoto, A. Hijikata, S. Yoshioka, A. Inoue: Improvement of fatigue strength in fillet welded joint by CO₂ soft plasma arc dressing on welded toe. IIW doc. XIII-881-78. July 1978.
25. M. Hanzawa, H. Yokota, T. Ishiguro: Improvement of fatigue strength in welded high tensile strength steel by toe treatment. Nippon Steel Corporation, IIW doc. XIII-829-77. *Welding Research International*, Vol. 8, No. 1. 1978.
26. K. Hoffmann, B. Muesgen: Improvement of the fatigue behaviour of welded high-strength steels by optimized shot peening. *Steel in Marine Structures*. Delft, 15–18 June 1987, p. 679.
27. A. Bignonnet, H.P. Lieurade, L. Picquet: Improvement of the fatigue life for offshore welded connections. 2nd International Conference on Welding of Tubular Structures. Boston. 16–17 July 1984, p. 271.
28. L. Picquet, A. Bignonnet, H.P. Lieurade: Influence de grenailage sur le comportement en fatigue d'assemblages soudés en acier HLE. IRSID RE 1041, Dec. 1983.
29. J.F. Flavenot, A. Andrzejewski, M. Bramat: Influence des traitements de parachèvement des soudures et de surcharge sur la tenue en fatigue des assemblages soudés. 9^e Journée Nationale sur le Grenailage de Précontrainte, CETIM, Senlis. 27 Nov. 1985. Journées de Printemps, Paris. 4–5 juin 1985. IIW doc. XIII-1160-85.
30. L. Picquet, A. Bignonnet, H.P. Lieurade, L. Castex, J.L. Lebrun: Influence du grenailage de précontrainte sur la tenue en fatigue d'assemblages soudés en acier HLE. Journées de Printemps, Paris, 4–5 juin 1985.
31. D. Albert, S. Bompard, M. Bramat, L. Castex: Influence d'un grenailage sur la tenue en fatigue des joints soudés en alliages d'aluminium. *Soudage et Techniques Connexes*, Vol. 45, No. 9/10, Sept/Oct. 1991.
32. D. Albert, S. Bompard, M. Bramat, L. Castex: Influence d'un post-traitement de grenailage sur la tenue en fatigue des joints soudés en alliages d'aluminium. 12^e Conférence Nationale sur le Grenailage de Précontrainte. CETIM, 25–26 Sept. 1991.
33. S. Kado, T. Ishiguro, M. Hanzawa, H. Yokota: Influence of the conditions in TIG dressing on fatigue strength in welded high tensile strength steels. Products Research and Development Laboratories, Nippon Steel Corporation, IIW doc. XIII-771-75.
34. J.O. Sperle, L. Bergovist: Influence of TIG dressing on the fatigue strength of cover plate beams. Institut International de la Soudure, Délégation suédoise, IIW doc. XIII-826-77.
35. J.L. Overbeeke, T.J. Alting, P.A.M. Jonkers: Influence of welded parameters on the fatigue strength under C.A. and V.A. loading of welded joints in HLSA steels. EIS 90 Conference Engineering Integrity Through Testing. Birmingham, 20–22 March 1990, IIW doc. XIII-1404-91. Technische Universiteit Eindhoven, Report LSF 89-146.
36. A. Bignonnet, L. Castex: Le choix des paramètres de grenailage de

- précontrainte en vue d'améliorer la tenue à la fatigue. 10^e Conférence sur le Grenaillage de Précontrainte, CETIM, Senlis, 17–18 Sept. 1986.
37. Sub-committee "Improving the fatigue strength of welded joints by various weld toe treatments": Methods of improving the fatigue strength of welded joints by various toe treatments. Society of Steel Construction of Japan, IIW doc. XIII-1289-88.
38. R. D'Haeyer, A. Bragard: Possibilité d'amélioration de la durée de vie des joints soudés par refusion TIG Conférence Internationale sur l'acier dans les structures marines, Paris, oct 1981.
39. P.J. Haagensen, A. Dragen, T. Slind, O. Ørjasaeter: Prediction of the improvement in fatigue life of welded joints due to grinding, TIG dressing, weld shape control and shot peening. *Steel in Marine Structures*, Delft, 15–18 June 1987, p. 609.
40. P.J. Haagensen: Résistance à la fatigue des joints soudés en acier après refusion TIG Conférence Internationale sur l'acier dans les structures marines, Paris, oct 1981.
41. A. Bignonnet: Résistance à la fatigue sous chargement d'amplitude variable de joints soudés grenailés RE 88316 dec. 1988 IIW-XIII-1308-89.
42. C.H. Mas, G. Brault, M. Bousseau: Rôle du grenaillage de précontrainte sur la tenue en fatigue et en fatigue corrosion de l'alliage 7075 soudé par faisceau d'électrons, IIW doc. XIII-1130-84.
43. G.S. Booth: Techniques for improving the corrosion fatigue strength of plate welded joints. *Steel in Marine Structures*, Delft, 15–18 June 1987, p. 747.
44. H.P. Lieurade, P. Castellucci, G. Bel, J. Lu, J.F. Flavenot: Tenue en fatigue d'assemblages soudés en acier HLE avec ou sans traitement de parachèvement Etude Corem/IS-CETIM 88-91 Rapport d'étude no 107900 CETIM, fev 1992.
45. A. Bignonnet, L. Picquet, H.P. Lieurade, L. Castex: The application of shot peening to improve the fatigue life of welded steel structures. *Steel in Marine Structures*, Delft, 15–18 June 1987, p. 669.
46. S. Kanazawa: The improvement of fatigue strength in welded high tensile strength steels. Nippon Steel Corporation, IIW doc. XIII-735-74.
47. A. Bignonnet, Y. Papadopoulos, F. Barrere, H.P. Lieurade, H. Lecoq: The influence of cathodic protection and post weld improvement on the fatigue resistance of steel welded joints. *Steel in Marine Structures*, Delft, 15–18 June 1987, p. 737.
48. P.J. Haagensen, P. Erasmo, B. Pettersen: Comportement à la fatigue dans l'air et dans l'eau de mer, et ténacité de joints en acier soudés après refusion TIG. European Offshore Steels Research, Cambridge, UK, 27–29 Nov. 1978.
49. Wildschut, J. de Back, W. Dortland, J.L. van Leuwen: Comportement en fatigue de joints soudés à l'air et dans l'eau de mer. European Offshore Steels Research, Cambridge, UK, 27–29 Nov. 1978.
50. J.L. van Leuwen, J. de Back, G.H.G. Vaessen: Essais de fatigue à amplitude constante dans l'air et dans l'eau de mer sur joints soudés (Constant amplitude fatigue tests on welded steel joints performed in air and sea water). Conférence Internationale sur l'acier dans les structures marines, Paris, Oct 1981.
51. S.J. Maddox: Improving the fatigue strength of welded joints by peening. *Metal Construction*, Vol. 17, No. 4, April 1985.
52. T. Pyle, M. Pitrum, P.H. Townend: Removal of fatigue damage in welded joints. Recent Trends in Welding Science and Technology, 2nd International Conference, Gatlinburg, 14–18 May 1989.
53. I.F.C. Smith, W.J. Muster, U. Bremen: Residual stresses and fatigue strength improvement of welded connections. The Effects of Fabrication related stresses on Product Manufacture and Performance, International Conference, Cambridge, UK, 23–25 Sept. 1985.
54. A. Tricotieux: Durée de fatigue de joints soudés en acier E690. Thèse, Ecole Centrale, Lille, 1993.
55. U. Bremen: Amélioration du comportement à la fatigue d'assemblage soudé: Etude et modélisation de l'effet de contraintes résiduelles. Thèse, no. 787, EPFIL, 1989.
56. U. Bremen, I.F.C. Smith, M.A. Hirt: Effet de contraintes résiduelles sur le comportement de fissures de fatigue dans un assemblage soudé et traité. *Construction Métallique*, No. 2, 1988.
57. S.J. Maddox, J.G. Summers: Preliminary investigation of the effect of controlled shot peening on the fatigue strength of fillet welded joints. Research Report, Welding Institute, Oct. 1980.
58. S.J. Maddox: Improving the fatigue lives of fillet welds by shot peening. Congrès IABSE, Lausanne, 1981.
59. Résultats d'essais de la SNCF.
60. H. Takenouchi, C. Miki, S. Sato: Fatigue performances of repairing welds with TIG-dressing for fatigue damage highway bridges. IIW doc. XIII-1509-93.
61. S. Ohta, K. Asai, S. Ohya: Root failure resulting from fillet toe dressing. IIW doc. XIII-1465-92.
62. B. Müsgen: Verbesserung der Schwingfestigkeit von Schweißverbindungen hochfester wasservergüterter Feinkombustähle durch thermische und mechanische Nachbehandlung der Nähte, EUR 7634 DE. 1982.

Improvement technique: Shot peening

	Butt joint (A)				T joint (C)				Cruciform (D)				Longitudinal (F)			
	<i>n</i>	Slope	$\Delta\sigma$	<i>s</i>	<i>n</i>	Slope	$\Delta\sigma$	<i>s</i>	<i>n</i>	Slope	$\Delta\sigma$	<i>s</i>	<i>n</i>	Slope	$\Delta\sigma$	<i>s</i>
Re < 400									66	9.16	194.1	28.0	26	4.64	119.7	14.3
400 < Re < 600	8	14.05	342.5	28.7	30	9.35	277.7	33.7								
Re > 600	99	10.7	330.5	52.7					33	8.78	227.7	39.5	18	4.94	147.3	13.8

Inferior envelope curves*Improvement technique: Hammer peening*

	Butt joint (A)			T joint (C)			Cruciform (D)			Longitudinal (F)		
	<i>n</i>	Slope	$\Delta\sigma$	<i>n</i>	Slope	$\Delta\sigma$	<i>n</i>	Slope	$\Delta\sigma$	<i>n</i>	Slope	$\Delta\sigma$
Re < 400	30	6.1	187				19	6.3	215	11	6.9	212
400 < Re < 600												
Re > 600												

Improvement technique: Grinding

	Butt joint (A)			T joint (C)			Cruciform (D)			Longitudinal (F)		
	<i>n</i>	Slope	$\Delta\sigma$	<i>n</i>	Slope	$\Delta\sigma$	<i>n</i>	Slope	$\Delta\sigma$	<i>n</i>	Slope	$\Delta\sigma$
Re < 400	30	7.4	201	18	3.5	73	9	7.7	149	45	4.2	122
400 < Re < 600							25	4.2	139	7	7.7	90
Re > 600							7	5.8	278			

Improvement technique: TIG dressing

	Butt joint (A)			T joint (C)			Cruciform (D)			Longitudinal (F)		
	<i>n</i>	Slope	$\Delta\sigma$	<i>n</i>	Slope	$\Delta\sigma$	<i>n</i>	Slope	$\Delta\sigma$	<i>n</i>	Slope	$\Delta\sigma$
Re < 400	65	5.4	215	25	3.1	129	48	4.1	128			
400 < Re < 600	156	3.9	184	74	3.2	149	154	4.2	252			
Re > 600												

Improvement technique: Shot peening

	Butt joint (A)			T joint (C)			Cruciform (D)			Longitudinal (F)		
	<i>n</i>	Slope	$\Delta\sigma$	<i>n</i>	Slope	$\Delta\sigma$	<i>n</i>	Slope	$\Delta\sigma$	<i>n</i>	Slope	$\Delta\sigma$
Re < 400							66	4	142	26	3	93
400 < Re < 600	8	5.3	240	30	7.7	236						
Re > 600	99	6	222				33	7.7	173	18	4.4	128